

RELIABILITY TEST RESULT

Product name : S-93C66BD0H -T8TxU

Package type : 8-Pin TSSOP

No.	Test item	Test Condition	Test Time	r/n	Criterion
1	High-temperature operation	Ta=125 °C, V=Vopr max.	1000 h	0/22	Satisfies the product standard
2	Temperature humidity bias ^{#1}	Ta=85 °C, RH=85 %, V=Vopr max.	1000 h	0/22	Satisfies the product standard
3	Pressure cooker bias ^{#1}	Ta=125 °C, RH=85 %, P=2×10 ⁵ Pa V = Vopr max.	100 h	0/22	Satisfies the product standard
4	Storage in high temperature	Ta=150 °C	1000 h	0/22	Satisfies the product standard
5	Storage in low temperature	Ta=-65 °C	1000 h	0/22	Satisfies the product standard
6	Write/Erase Cycle -1	Ta=85 °C, V =Vopr max.	1×10 ⁶ cycles	0/22	Satisfies the product standard
7	Write/Erase Cycle -2	Ta=105 °C, V =Vopr max.	5×10 ⁵ cycles	0/22	Satisfies the product standard
8	Temperature Cycle (Gas phase) ^{#1}	Ta=150 °C ⇔ -65 °C 15 minutes for each	500 cycles	0/22	Satisfies the product standard
9	Resistance to soldering heat-1 (reflow soldering) ^{#2}	T=260 °C ,10 s	3 times	0/22	Satisfies the product standard No abnormality by appearances
10	Resistance to soldering heat-2 (Soldering Iron) ^{#2}	T=380 °C , 5 s (Soldering iron tip temperature) Object : terminal parts	2 times	0/22	Satisfies the product standard No abnormality by appearances
11	Resistance to soldering heat - 3 (Flow soldering) ^{#2}	T=260 °C ,10 s	1 time	0/22	Satisfies the product standard No abnormality by appearances
12	Solderability ^{#3}	T=245 °C Solder material : Sn-3.0Ag-0.5Cu	5 s	0/11	Zero cross time should be less than 3 seconds. Solder should be applied at 95% or more of solderability judgment area.
13	Whisker - 1 (Temperature / Humidity Storage)	Ta=30 °C, RH=60%	4000 h	0/6	Whisker should be less than 40μm
14	Whisker - 2 (Temperature Cycling)	Ta=85 °C ⇔ -40 °C	1500 cycles	0/6	Whisker should be less than 45μm
15	Whisker - 3 (High Temperature / Humidity Storage)	Ta=55 °C, RH=85 %	4000 h	0/6	Whisker should be less than 40μm
16	Solder Joint Reliability (shear test) ^{#3}	Ta=125 °C ⇔ -40 °C Solder material : Sn-3.0Ag-0.5Cu	2000 cycles	0/22	After temperature cycle test, keep strength for shear stress more than the 50 % of initial mean value.
17	Terminal Strength (Pull test)	Pull force : 1.0 N	30 s	0/11	Terminal is not taken off
18	Terminal Strength (Bending test)	Load : 0.5 N, 45 degree Bend a lead	2 times	0/11	Terminal is not taken off
19	ESD - 1 (Human Body Model)	V=±2000 V, C=100 pF, R=1.5 kΩ Ground : V _{CC} / GND	5 pulses	0/5	Satisfies the product standard
20	ESD - 2 (Charged Device Model)	V=±500V charged, discharged	1 pulse	0/5	Satisfies the product standard
21	Latch up (Pulsed current injection test)	±100 mA, V =Vopr max.	1 pulse	0/5	No latch up

Remark : Vopr max. =Maximum operation voltage

#1,2,3 : Each test designated # is performed after Pre-Treatment finished.

Pre-Treatment consists of High Temperature Storage ,Temperature Humidity Storage and Soldering Heat. (See the table below.)

Pre Treatment (#1)		
High Temp. Storage	Temperature Humidity Storage	Soldering Heat
Ta=125 °C t=24 h	Ta=85 °C RH=85 % t=168 h	Reflow 3 times T=260 °C t=10 s

Pre Treatment (#2)		
High Temp. Storage	Temperature Humidity Storage	Soldering Heat
Ta=125 °C t=24 h	Ta=85 °C RH=85 % t=168 h	—

Pre Treatment (#3)		
High Temp. Storage	Temperature Humidity Storage	Soldering Heat
—	Ta=105 °C RH=100 % t=8 h	—